



PTO/SB/21 (08-03)

Approved for use through 07/31/2006. OMB 0651-0031

U.S. Patent and Trademark Office: U.S. DEPARTMENT OF COMMERCE

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number.

TRANSMITTAL FORM (to be used for all correspondence after initial filing)	Application Number	10/666,618	
	Filing Date	September 18, 2003	
	First Named Inventor	LEE, Bong Ryeol	
	Art Unit	1755	
	Examiner Name	James W. Pasterczyk	
Total Number of Pages in This Submission	1	Attorney Docket Number	29137.028.00-US

ENCLOSURES (Check all that apply)

<input type="checkbox"/> Fee Transmittal Form <input type="checkbox"/> Fee Attached <input type="checkbox"/> Amendment/Reply <input type="checkbox"/> After Final <input type="checkbox"/> Affidavits/declaration(s) <input type="checkbox"/> Extension of Time Request <input type="checkbox"/> Express Abandonment Request <input type="checkbox"/> Information Disclosure Statement <input type="checkbox"/> Certified Copy of Priority Document(s) <input type="checkbox"/> Response to Missing Parts/ Incomplete Application <input type="checkbox"/> Response to Missing Parts under 37 CFR 1.52 or 1.53	<input type="checkbox"/> Drawing(s) <input type="checkbox"/> Licensing-related Papers <input type="checkbox"/> Petition <input type="checkbox"/> Petition to Convert to a Provisional Application <input type="checkbox"/> Power of Attorney, Revocation Change of Correspondence Address <input type="checkbox"/> Terminal Disclaimer <input type="checkbox"/> Request for Refund <input type="checkbox"/> CD, Number of CD(s) _____	<input type="checkbox"/> After Allowance Communication to Group <input type="checkbox"/> Appeal Communication to Board of Appeals and Interferences <input type="checkbox"/> Appeal Communication to Group (Appeal Notice, Brief, Reply Brief) <input type="checkbox"/> Proprietary Information <input type="checkbox"/> Status Letter <input checked="" type="checkbox"/> Other Enclosure(s) (please identify below): Declaration of Dr. Bun Yeoul Lee
Remarks		

SIGNATURE OF APPLICANT, ATTORNEY, OR AGENT

Firm or Individual name	Song K. Jung; Reg No. 35,210 MCKENNA LONG & ALDRIDGE LLP
Signature	<i>Yach P. Kusloff</i> #42,7166
Date	September 6, 2005



MUTU11.001CP1

PATENT

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

Applicant	: Lee, et al.
Appl. No.	: 10/666,618
Filed	: September 18, 2003
For	: SUPPORTED METALLOCENE CATALYST AND OLEFIN POLYMERIZATION USING THE SAME
Examiner	: Pasterczyk, J. W.
Group Art Unit	: 1755

DECLARATION OF BUN YEOUL LEE

United States Patent and Trademark Office
P.O. Box 2327
Arlington, VA 22202

Dear Sir:

I, Dr. Bun Yeoul Lee, declare as follows:


1. I am one of the inventors of the subject application. I have a Ph.D. of Seoul National University in the department of chemistry and many years of experience working in research and development on olefin polymerization catalysts. I am currently an assistant manager in Technology Center of LG Chemical Ltd.

2. I am familiar with the prosecution of the present application, including the Office Action mailed October 15, 2004, the references cited therein, and the Amendment accompanying this Declaration.

3. I am advised that pending Claims 4-10 and 15-20 have been rejected as obvious over as obvious over any of Korean Laid-Open Patent 98-25282 (hereinafter "Lee II"), US 5,814,574 (hereinafter "McNally"), EPO 0 839 836 (hereinafter "Sancho Royo"), and U.S. Publ. No. 2003/0144135 A1 (hereinafter "Llinas et al.").

4. I and my co-inventors have developed olefin polymerization catalysts that exhibit unexpectedly superior activity when compared to conventional olefin polymerization catalysts.

Unlike conventional catalysts, the catalysts of the present invention use a specific, functionalized metallocene compound reacted with a dehydroxylated silica support material to produce a supported metallocene catalyst:



The metallocene catalyst includes a moiety of formula A'-O, wherein A' is a carbon-based group such as tert-butyl or tetrahydropyranyl, that reacts with a reactive siloxane (Si-O-Si) group of the support material to produce a supported metallocene catalysts exhibiting unexpectedly superior activity and which are prepared by a method that does not result in formation of undesirable reaction by-products such as alcohol. The supported catalysts exhibit reduced reactor fouling, superior activity, and yield a better defined bulk density of polymer when compared to metallocenes containing other alkoxy groups, as discussed in the Examples of the present application.

5. Table 1 provides experimental data including measurements of catalyst activity (as kg of polyethylene produced per mmol of zirconium in the catalyst) of five different catalysts according to our invention. As the data demonstrate, the type of functional group included in the metallocene compound can have a significant effect on activity of the supported catalyst prepared from it. When a functional group (X) is a tert-butyl consisting of only carbon and hydrogen without a heteroatom such as oxygen, its supported catalyst (Example 5) is especially active for ethylene polymerization. We have also discovered that functional groups of the formula -C-OX can be incorporated into the metallocene compound to yield supported catalysts that also exhibit particularly good activity. Such catalysts include those incorporating a moiety of Chemical Formula 1 as depicted in the present application, wherein the Z atom is bonded to a silicon atom of a siloxane group (Si-O-Si) in the dehydroxylated silica support and the radical portion (X = -CR'₂G) is bonded to an oxygen atom of the siloxane group. Our supported catalysts where X (-CR'₂G) include only carbon and hydrogen atoms, for example, a hydrogen, an alkyl, cycloalkyl,

Appl. No. : 10/666,618
 Filed : September 18, 2003


aryl, alkenyl, alkylaryl, arylalkyl, or arylalkenyl radical having up to 20 carbon atoms, or a phenyl or substituted phenyl, are especially active for olefin polymerization.

Table 1.

	Functional Group (A')	Zr (mmol)	Al/Zr ratio	Activity (kg PE / mmol Zr)
Example 1	[MeOCH ₂ O(CH ₂) ₆ Cp] ₂ ZrCl ₂	0.0156	64	3.40
Example 2	[MeC(Me)(OMe)O(CH ₂) ₆ Cp] ₂ ZrCl ₂	0.0143	70	4.90
Example 3	[(C ₃ H ₉ O)O(CH ₂) ₆] ₂ ZrCl ₂	0.0137	73	5.84
Example 4	[MeCH(OEt)O(CH ₂) ₆ Cp] ₂ ZrCl ₂	0.0143	70	5.52
Example 5	[Me ₃ CO(CH ₂) ₆ Cp] ₂ ZrCl ₂	0.0150	67	6.73

(Polymerization conditions: temp. 80 °C, MAO (Al) 1.0 mmol, C2 pressure 9 bar)

6. In contrast to the catalysts of the present invention, conventional catalysts such as those disclosed in EPO 0 839 836 incorporate a functional group of formula -C-SiR₂X (X = alkoxy) in which the silicon atom is bonded to an oxygen atom of a silanol group in the silica support surface and the radical portion (X = alkoxy) reacts with a hydrogen of the silanol group of a hydroxylated silica support to yield a free alkyl alcohol (XH). Polymerization activity results for examples of such supported metallocene systems are provided in Table 2. Side reactions can occur during preparation of such catalysts, however, such as the following reaction:



Such side reactions can result in leaching when activated with methylalumoxane. Accordingly, while an R'O-Si group on the metallocene compound can react with an Si-OH group of the hydroxylated silica support to produce a strongly-bound, supported metallocene catalyst via Si-O-Si bond formation, alkyl alcohol (R'O-H) is also formed as by-product during the reaction, which can act as a catalyst poison to lower activity of the final catalyst, and can result in substantial catalyst fouling. Such by-products are not produced in the reaction used to prepare the catalysts of our invention.

Table 2.

	Metal (mmol)	Al/Metal ratio	Activity (kg PE / mmol Metal)
Comparative Example 1	Zr, 0.02	11	3.03
Comparative Example 2	Zr, 0.01	22	4.2
Comparative	Ti, 0.02	11	1.4


Appl. No. : 10/666,618
 Filed : September 18, 2003

Example 3			
Comparative Example 4	Hf, 0.02	11	0.6

(Polymerization conditions: temp. 70 °C, MAO (Al) 0.22 mmol, C2 pressure 7 bar)

7. Catalysts have been prepared according to the teachings of Lee II, McNally, Sancho Royo, and Llinas et al. A catalyst prepared according to the method of Lee II exhibited an activity of 1.51 kg PE / mmol Zr hr. A catalyst prepared according to the method of McNally exhibited an activity of 0.40 kg PE / mmol Zr hr. A catalyst prepared according to the method of Sancho Royo exhibited an activity of 3.05 kg PE / mmol Zr hr. A catalyst prepared according to the method of Llinas et al. exhibited an activity of 3.24 kg PE / mmol Zr hr. These activities are substantially less than those of the most active catalysts of our invention.

8. We have also discovered that the length of the carbon chain between the Cp ring and the active functional group can affect catalyst activity. Table 3 provides activities of supported catalysts produced by reaction of a functionalized metallocene compound of formula:



wherein A' is tert-butyl, and a dehydroxylated silica (dried at 800°C). As demonstrated by the data, a carbon chain length (n) of 4 to 8 unexpectedly results in a supported catalyst that is especially active for ethylene polymerization, in contrast to the only trace activity of a catalyst where the carbon chain length (n) is 2.

Table 3.

Example ¹	Carbon Length (n)	Yield (g)	Activity ²	Mw	Mw/Mn
1	C2	Trace	-	-	-
2	C4	2.50	100	133,780	2.60
3	C6	5.80	232	147,390	2.61
4	C8	2.74	110	92,830	3.02

¹ condition: 500 mL Endrew glass, T_p=80°C; t=30 min; p(C₂H₄)=4.0 bar, cat.=50 mg, mole ratio Al/Zr=500

² g PE / g Cat · hr

Appl. No. : 10/666,618
Filed : September 18, 2003

9. I declare that all statements made herein are true, and that all statements made upon information and belief are believed to be true, and further, that these statements were made with the knowledge that willful, false statements and the like so made are punishable by fine or imprisonment, or both, under 18 U.S.C. § 1001, and that willful, false statements may jeopardize the validity of the application, or any patent issuing thereon.

Dated: 18/08/2005 By: Lee Bum Jeoul

S:\DOCS\RMTRMT-6410.DOC
021105